

	Type	Hits	Search Text
1	BRS	532	429/128,137,302.ccls.
2	BRS	18831	size near3 (projection protrusion)
3	BRS	48892	kao.as.
4	BRS	5	S14 and ((thin adj film) with negative adj electrode)
5	BRS	8	S12 and "429"/\$.ccls.
6	BRS	424	(current adj collector) with (projection protrusion)
7	BRS	305	(anode (negative adj electrode)) with (amorphous adj silicon)
8	BRS	14	S17 and S22
9	BRS	11	S20 and @ad<"20021227"
10	BRS	17	S17 and S19
11	BRS	24181	diameter near3 (projection protrusion)

	DBs
1	US-PGPUB; USPAT; USOCR; EPO; JPO; DERWENT
2	US-PGPUB; USPAT; USOCR; EPO; JPO; DERWENT
3	US-PGPUB; USPAT; USOCR; EPO; JPO; DERWENT
4	US-PGPUB; USPAT; USOCR; EPO; JPO; DERWENT
5	US-PGPUB; USPAT; USOCR; EPO; JPO; DERWENT
6	US-PGPUB; USPAT; USOCR; EPO; JPO; DERWENT
7	US-PGPUB; USPAT; USOCR; EPO; JPO; DERWENT
8	US-PGPUB; USPAT; USOCR; EPO; JPO; DERWENT
9	US-PGPUB; USPAT; USOCR; EPO; JPO; DERWENT
10	US-PGPUB; USPAT; USOCR; EPO; JPO; DERWENT
11	US-PGPUB; USPAT; USOCR; EPO; JPO; DERWENT

	Type	Hits	Search Text
12	BRS	96	S10 and ((electron adj beam adj evaporation) (vapor adj deposition))
13	BRS	45	S11 and @ad<"20021227"
14	BRS	8	S23 and @ad<"20021227"
15	BRS	32	S60 and @ad<"20021227"
16	BRS	288	S65 and @ad<"20021227"
17	BRS	39	S66 and (lithium adj3 battery)
18	BRS	2	"6242132".pn. and (cu copper substrate)
19	BRS	12971	(anode (negative adj electrode)) with (silicon)
20	BRS	9	(electrochemical adj hydrogen adj separator) with membrane
21	BRS	61	S42 and "429"/\$.ccls.
22	BRS	63	S58 and (protrusion projection bump indentation)

	DBs
12	US-PGPUB; USPAT; USOCR; EPO; JPO; DERWENT
13	US-PGPUB; USPAT; USOCR; EPO; JPO; DERWENT
14	US-PGPUB; USPAT; USOCR; EPO; JPO; DERWENT
15	US-PGPUB; USPAT; USOCR; EPO; JPO; DERWENT
16	US-PGPUB; USPAT; USOCR; EPO; JPO; DERWENT
17	US-PGPUB; USPAT; USOCR; EPO; JPO; DERWENT
18	US-PGPUB; USPAT; USOCR; EPO; JPO; DERWENT
19	US-PGPUB; USPAT; USOCR; EPO; JPO; DERWENT
20	US-PGPUB; USPAT; USOCR; EPO; JPO; DERWENT
21	US-PGPUB; USPAT; USOCR; EPO; JPO; DERWENT
22	US-PGPUB; USPAT; USOCR; EPO; JPO; DERWENT

	Type	Hits	Search Text
23	BRS	76	reversible adj fuel adj cell
24	BRS	40	S46 and "429"/\$.ccls.
25	BRS	6	S66 and ((electron adj beam adj evaporation) (vapor adj deposition))
26	BRS	1	"6242163".pn. and (cu copper substrate)
27	BRS	76	S46 and (fuel adj cell)
28	BRS	38	S59 and (lithium adj3 battery)
29	BRS	454	(current adj collector) with (protrusion projection bump indentation)
30	BRS	6	PBI adj ion adj exchange adj membrane
31	BRS	42	S43 and amorphous
32	BRS	596	S58 and @ad<"20021227"
33	BRS	564	S62 not S61

	DBs
23	US-PGPUB; USPAT; USOCR; EPO; JPO; DERWENT
24	US-PGPUB; USPAT; USOCR; EPO; JPO; DERWENT
25	US-PGPUB; USPAT; USOCR; EPO; JPO; DERWENT
26	US-PGPUB; USPAT; USOCR; EPO; JPO; DERWENT
27	US-PGPUB; USPAT; USOCR; EPO; JPO; DERWENT
28	US-PGPUB; USPAT; USOCR; EPO; JPO; DERWENT
29	US-PGPUB; USPAT; USOCR; EPO; JPO; DERWENT
30	US-PGPUB; USPAT; USOCR; EPO; JPO; DERWENT
31	US-PGPUB; USPAT; USOCR; EPO; JPO; DERWENT
32	US-PGPUB; USPAT; USOCR; EPO; JPO; DERWENT
33	US-PGPUB; USPAT; USOCR; EPO; JPO; DERWENT

	Type	Hits	Search Text
34	BRS	65	S63 and ((electron adj beam adj evaporation) (vapor adj deposition))
35	BRS	11	S37 and "nabh.sub.4"
36	BRS	5	S34 and ((deposition))
37	BRS	1	S34 and ((electron adj beam adj evaporation) (vapor adj deposition))
38	BRS	0	S43 and ("sib.sub.4" "sib.sub.6" "mg.sub.2si" "ni.sub.2si0")
39	BRS	0	S50 not S49
40	BRS	11	S56 and @ad<"20021227"
41	BRS	3931	gas adj generator.clm.
42	BRS	14	S55 same (electron adj beam adj evaporation)
43	BRS	795	(current adj collector) with adhesion
44	BRS	1	S35 and ((electron adj beam adj evaporation) (vapor adj deposition))

	DBs
34	US-PGPUB; USPAT; USOCR; EPO; JPO; DERWENT
35	US-PGPUB; USPAT; USOCR; EPO; JPO; DERWENT
36	US-PGPUB; USPAT; USOCR; EPO; JPO; DERWENT
37	US-PGPUB; USPAT; USOCR; EPO; JPO; DERWENT
38	US-PGPUB; USPAT; USOCR; EPO; JPO; DERWENT
39	US-PGPUB; USPAT; USOCR; EPO; JPO; DERWENT
40	US-PGPUB; USPAT; USOCR; EPO; JPO; DERWENT
41	US-PGPUB; USPAT; USOCR; EPO; JPO; DERWENT
42	US-PGPUB; USPAT; USOCR; EPO; JPO; DERWENT
43	US-PGPUB; USPAT; USOCR; EPO; JPO; DERWENT
44	US-PGPUB; USPAT; USOCR; EPO; JPO; DERWENT

	Type	Hits	Search Text
45	BRS	12971	(anode (negative adj electrode)) with (silicon)
46	BRS	21	S33 and @ad<"20021227"
47	BRS	46	(anode (negative adj electrode)) same ("sib.sub.4" "sib.sub.6" "mg.sub.2si" "ni.sub.2si0")
48	BRS	13	S31 and @ad<"20021227"
49	BRS	61	S42 and "429"/\$.ccls.
50	BRS	29	S30 and ((electron adj beam adj evaporation) (vapor adj deposition))
51	BRS	275	(anode (negative adj electrode)) same ((silicon adj compound))
52	BRS	643	S27 and ((electron adj beam adj evaporation) (vapor adj deposition))
53	BRS	1738	S39 and ((electron adj beam adj evaporation) (vapor adj deposition))
54	BRS	12	(anode (negative adj electrode)) same ("sib.sub.4" and "sib.sub.6")
55	BRS	3	S25 and @ad<"20021227"

	DBs
45	US-PGPUB; USPAT; USOCR; EPO; JPO; DERWENT
46	US-PGPUB; USPAT; USOCR; EPO; JPO; DERWENT
47	US-PGPUB; USPAT; USOCR; EPO; JPO; DERWENT
48	US-PGPUB; USPAT; USOCR; EPO; JPO; DERWENT
49	US-PGPUB; USPAT; USOCR; EPO; JPO; DERWENT
50	US-PGPUB; USPAT; USOCR; EPO; JPO; DERWENT
51	US-PGPUB; USPAT; USOCR; EPO; JPO; DERWENT
52	US-PGPUB; USPAT; USOCR; EPO; JPO; DERWENT
53	US-PGPUB; USPAT; USOCR; EPO; JPO; DERWENT
54	US-PGPUB; USPAT; USOCR; EPO; JPO; DERWENT
55	US-PGPUB; USPAT; USOCR; EPO; JPO; DERWENT

	Type	Hits	Search Text
56	BRS	2062	(anode (negative adj electrode)) same ((silicon adj oxide))
57	BRS	105	"5011501" and anode
58	BRS	1	"5011501".pn. and microroughened
59	BRS	2	"5011501".pn. and anode
60	BRS	0	"5011501".pn. and microroughtened
61	BRS	22	("5011501").URPN.
62	BRS	0	"5011501.pn." and cathode
63	BRS	0	"5011501.pn." and anode

	DBs
56	US-PGPUB; USPAT; USOCR; EPO; JPO; DERWENT
57	US-PGPUB; USPAT; USOCR; EPO; JPO; DERWENT
58	US-PGPUB; USPAT; USOCR; EPO; JPO; DERWENT
59	US-PGPUB; USPAT; USOCR; EPO; JPO; DERWENT
60	US-PGPUB; USPAT; USOCR; EPO; JPO; DERWENT
61	USPAT
62	US-PGPUB; USPAT; USOCR; EPO; JPO; DERWENT
63	US-PGPUB; USPAT; USOCR; EPO; JPO; DERWENT